

Please visit our new website and give us your feedback : <http://www.suszi.ro>

BENZI DE FRANARE

Trimat – Anglia

Produse standard :

1. Benzi de franare impletite, cu fibre naturale si sintetice

Tip de banda de franare	Coeficient de frecare	Temperatura °C	
		Maxim continuu	Maxim intermitent
1. GBC – cu insertie de alama	0.46	150	230
2. GZC – cu insertie de zinc	0.41	150	230
3. CNB – fibre de bumbac, fara insertie	0.60	90	130
4. CNC – fibre sintetice de bumbac, fara insertie	0.45	100	175

2. Benzi de franare matritate (turnate)

Tip de banda de franare	Coeficient de frecare	Temperatura °C	
		Maxim continuu	Maxim intermitent
1. MR 8728 –flexibil, in totalitate acoperit	0.38	250	350
2. MR 7032 - flexibil, in totalitate acoperit	0.41	250	300
3. MR 2925 – flexibil, semi-acoperit	0.39	250	350
4. MR 2925 W/B – flexibil, semi-acoperit	0.38	250	350

3. Benzi de franare matritate (presate)

Tip de banda de franare	Coeficient de frecare	Temperatura °C	
		Maxim continuu	Maxim intermitent
1. MN 1042 – presata, rigida	0.15	175	350
2. MN 1046 – presata, rigida	0.37	300	400
3. MN 1050 - presata, rigida	0.40	300	400